

**TECHNICAL DATA SHEET****Product Description**

<i>PROPERTY</i>	<i>TEST METHOD</i>	<i>UNITS</i>	<i>VALUE</i>
Elongation at Break	ISO 527	%	>50
Flexural Modulus	ISO 178	Mpa	2200
Tensile Modulus	ISO 527	Mpa	2250
Tensile Yield Strength	ISO 527	Mpa	53
Izod Impact (notched) @ 23°C	ASTM D256	Kj/m <sup>2</sup>	40
Izod Impact (unnotched) @ -20°C	ASTM D256	Kj /m <sup>2</sup>	25
Density	ISO 1183	g/cm <sup>3</sup>	1.13
Melt Flow Rate (260°C / 5Kg)	ISO 1133	g/10min	20
Heat Distortion Temperature - @ 0.45Mpa	ISO 75-2	°C	123
Heat Distortion Temperature - @ 1.8 Mpa	ISO 75-2	°C	100
Vicat Softening Point (5Kg/50°C/Hr)	ISO 306 B	°C	121
Flammability @ 3.2mm thickness	UL94 EQUIVALENT	Rating	HB

**Additional Information**

JGP/Perrite manufacture a wide range of engineering thermoplastic compounds with filled flame retardant, impact modified variants available. All grades can be colour matched to meet specific customer requirements.

The information in this publication is based on our present technical knowledge and experience. In view of the large number of factors which may influence the processing and use of our products, the present information does not relieve processors and manufacturers of the need to carry out their own tests and experiments.